TECHNICAL DATA SHEET

Ultramarine Pigment



Pigment Blue 464

Edition of	2016-12-16
Туре	Blue pigment
Delivery Form	Powder
Chemical Class	Na6Al4Si6S4O20
Color Index	Pigment Blue 29 (77007)
CAS No.	57455-37-5

COLOR VALUES AND TINTING STRENGTH

Reference DIN 55986 (1981) Standard Reduction with titanium dioxide (1:2) colour values after matching of the tinting strength parameter

	Min	Max	Test Method
$\triangle L^*$	-0.7	+0.7	
$ riangle \mathbf{a}^{\star}$	-0.7	+0.7	
$ riangle { b}^{\star}$	-0.7	+0.7	
∆E*ab		1.0	
Relative tinting strength [%]	95	105	

TECHNICAL DATA

	Min	Max	Test Method
Water-Soluble Content [%]		1.5	DIN EN ISO787 Part 3 (1995)
Sieve Residue (0.045mm) [%]		0.1	DIN 53195 (1990)
PH Value	7.5	10	DIN EN ISO787 Part 9 (1995)
Free Sulfur [%]		0.10	DIN 55913 (1972)
105°CMoisture (After Production) [%]		1.0	DIN EN ISO 787 Part 2 (1995)
Oil Absorption [g/100g]	25.0	45.0	DIN EN ISO787 Part 5 (1995)

TECHNICAL DATA SHEET

Ultramarine Pigment



Pigment Blue 464

STANDARD PACKAGING 25kg/bag

TRANSPORT AND STORAGE

Protect against weathering. Store in a dry place and avoid extreme fluctuations in temperature. Special conditions for opened packaging: Close bags after use to prevent the absorption of moisture and contamination.

SAFETY

The product is not classified as dangerous under the relevant EC directives and corresponding national regulations valid in the individual EU member states. It is not dangerous according to transport regulations. In countries outside the EU, compliance with the respective national legislation concerning the classification, packaging, labeling and transport of dangerous substances must be ensured. The information contained in the safety data sheet should be observed. This contains information on handing, product safety and ecology.

This information is given in good faith, without warranty. It is also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General conditions of sale and delivery.

HANGZHOU XCOLOR Tel:86-571-83885088 Fax:86-571-83885208 www.xcolor.net Email: sales@xcolor.net info@xcolor.net